



gloveon Matador

Nitrile Exam Gloves Powder Free, Long Cuff

GloveOn® Matador is built with quality, consistency and reliability in an 8ml nitrile glove. With GloveOn® Matador, users can take confidence in wearing a stronger glove to shape their performance in their work duties.



Physical Dimensions	
Length (mm)	≥ 280
Palm Thickness (mm)	0.20 ± 0.04
Finger Thickness (mm)	0.28 ± 0.04
Cuff (25mm from cuff edge)	0.14 ± 0.04
Physical Properties	
Tensile Strength (MPa)	Before Ageing: ≥ 18, After Ageing: ≥ 16
Elongation (%)	Before Ageing: ≥ 500, After Ageing: ≥ 400
Inspection Levels & AQL	
Watertightness	Inspection Level: G1, AQL: 1.5
Physical Dimensions	Inspection Level: S2, AQL: 4.0
Tensile Strength	Inspection Level: S2, AQL: 4.0
Visual Inspection (Major)	Inspection Level: S4, AQL: 2.5
Visual Inspection (Minor)	Inspection Level: S4, AQL: 4.0
Particulate Residue	Inspection Level: N = 5, AQL: ≤ 2mg/glove

REORDER CODE

NTR18SS	SMALL
NTR18MM	MEDIUM
NTR18LL	LARGE
NTR18XL	X-LARGE

FEATURES

- Fingertip textured • Powder free
- Not made with natural rubber latex
- Chemo drugs tested
- Lab chemical tested • Ambidextrous
- Long cuff • Sky blue colour

PACKAGING

50 gloves per box for S to XL
10 boxes per carton

REGULATORY COMPLIANCE

ARTG 164563, FDA 510(k),
MDD 93/42/EEC, REACH,
ROHS Directive 2002/95/EC, EU 2016/425

STANDARDS

AS/NZS 4011-1, ASTM D6319, ASTM D5151,
ASTM D6124, ASTM D6978, EN 420,
EN 16523-1, EN ISO 374-1 (Type A),
EN 374 part 2, 4 & 5, ISO 11193-1,
EN 455 part 1, 2, 3 & 4, ISO 10993 part 5 & 10,
HACCP Certified

MANUFACTURING ACCREDITATIONS ISO

9001, ISO 13485

Chemotherapy Drugs and Concentration (Tested for Resistance to Permeation by Chemotherapy Drugs as per ASTM D6978-05-Test Report PN 107200B)	Minimum Breakthrough Detection Time (minutes)
Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	90.6 minutes
Cisplatin, 1.0mg/ml (1,000 ppm)	>240 minutes
Cyclophosphamide (Cytoxan), 20.0mg/ml (20,000 ppm)	>240 minutes
Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)	>240 minutes
Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)	>240 minutes
Etoposide (Toposar), 20.00mg/ml (20,000 ppm)	>240 minutes
Fluorouracil, 50.0mg/ml (50,000 ppm)	>240 minutes
Methotrexate, 25.0mg/ml (25,000 ppm)	>240 minutes
Mitomycin C, 0.5mg/ml (500 ppm)	>240 minutes
Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)	>240 minutes
Thiotepa, 10.0mg/ml (10,000 ppm)	165.8 minutes
Vincristine Sulfate, 1.0mg/ml (1,000 ppm)	>240 minutes

WARNING: Carmustine and Thiotepa, at the tested concentration, degraded Matador nitrile glove at 90.6 minutes and 165.8 minutes, respectively. The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

Measured breakthrough time (minutes)	>10	>30	>60	>120	>240	>480
Permeation performance level	1	2	3	4	5	6

Chemical	EN 16523-1:2015 Permeation Level	EN 374-4:2013 Mean Degradation (%)
J n-Heptane	3	36.5
K 40% Sodium Hydroxide	6	-1.8
L 96% Sulphuric Acid	2	100.0
O 25% Ammonium Hydroxide	4	46.9
P 30% Hydrogen Peroxide	6	20.4
T 37% Formaldehyde	6	22.3
S 40% Hydrofluoric Acid	2	n/a

A brand by



Mun Australia
Toll free: 1800 456 837
munglobal.com.au



Proud Supporter of
Birthing Kit Foundation (Australia)

